



single-component additives

Functions:

It is used to accelerate the hardening of penetrations, plastic concrete, plastic mortar, grouting, etc.

Advantages:

- cost savings for downtime
- faster commissioning of the surface
- possible implementation at lower temperatures

Packaging and coverage:

The stated consumption of materials may vary according to specific conditions and specific application.

Retail packaging	1 kg
Wholesale packaging	5 kg

Possible applications:

- acceleration of TopStone series products EP01, EP02 and EP01-EKO, EP02-EKO, Topfix

Properties:

-clear to yellowish low-viscosity additive for epoxies, solvent-free

Instructions for use:

	Accelerator B comp. dosing	Non-sticky, finally grindable, paintable		Hard, grindable	
		16°C	23°C	16°C	23°C
Thin coating	max. 10 %	6 hod.	5 hod.	8 hod.	7 hod.
Rough coating, reprofiling	max. 10 %	5 hod.	3,5 hod.	7 hod.	6 hod.
Polymer concrete approx. 1cm	max. 10 %	3 hod.	2,5 hod.	6 hod.	5 hod.

ATTENTION: When applying a larger dose of Accelerator than recommended, there will be a slight deviation in the shade of the pigmented penetrations, and the other parameters of the material cannot be guaranteed either.

For example, 10% acceleration of mass EP02: mixing ratio of mass EP02 A:B = 1.8:1 - mixed quantity 2.8kg = Sl.A-1.8kg and Sl.B-1kg + TopStone Accelerator 10% from sl. B = 0.1 kg. That is the total mixed quantity is 2.9 kg of mass.

Attention!!! Since the resulting hardening of the product is accelerated, the processing time for the given product that we accelerate is shortened. After mixing, apply immediately, if necessary, mix in smaller amounts. Depending on the temperature, the processing time can be shortened to 10 minutes.

Storage:

At temperatures > +12°C < +25°C, dry, in original packaging. Warranty period see information on the packaging.

TOPSTONE s.r.o.
Družstevní 442, Hranice, 753 01
Česká republika
+420 580 582 580 | info@topstone.cz
stavebnichemie.topstone.cz

ISO 9001, ISO 14001

Slovenská republika
TOPSTONE Slovensko s.r.o.
prevádzka Vrbovská cesta 123
921 01 Piešťany
+421 918 459 563 | info@topstone.sk
stavebnachemia.topstone.sk

PARTNER / SELLER: