



# PURSTONE ONE VITAL

24.05.2024 | VERSION 1

Polyurethane one-component revitalizing coating with excellent UV stability

## ADVANTAGES

- Excellent UV stability - does not yellow
- High chemical resistance - salt water
- Weather resistance
- Exterior and interior use
- Extension of surface life

## SPECIFICATIONS

### Possibility of use:

Revitalization of stone carpets on horizontal surfaces in exterior and interior.

Suitable for all types of aggregates - river and marble.

Suitable for light shades of marble in the exterior.

Suitable for revitalising stone carpets around saltwater swimming pools.

Suitable for revitalisation of the original binder - EpoStone, PurStone One.

### Restrictions:

The aggregate must be dry. Wet aggregate can cause the binder to foam. The surface must be cleaned, free of dust, dirt and grease before applying the revitalizing coating. Attention to binder consumption!

### Packaging:

Retail 1 kg

### Storage:

12 months from the date of manufacture at temperatures of +5 °C to +25 °C, in the original packaging in a shaded place.

Use the opened packaging as soon as possible (the binder reacts with humidity).

## APPLICATION PART

### Preparing the substrate:

Remove dirt and incoherent parts from the substrate and clean it with high-pressure equipment. Remove grease stains or other chemical contamination with acetone as follows. Pour the acetone into a paint tray, dip a stiff rice brush into the acetone, let it drain and then clean the surface. Repeat this until the entire surface is thoroughly cleaned. Acetone must never be poured on the surface! Allow the cleaned surface to dry for 2 - 3 days.

### Application:

Shake the binder thoroughly for at least 2 minutes. Pour the shaken binder into the prepared paint tray. Apply the material with a roller or brush. Never pour the material into the stones.

Always remove excess binder by wiping the roller on the paint grid before use. The consumption per 1 m<sup>2</sup> is 0.2 kg/m<sup>2</sup>.

### Attention:

PurStone One Vital must not come into direct contact with water or other chemicals during application and curing. Moisture significantly affects curing. Pay attention to the dew point, the air and substrate temperature must be at least +3 °C above the dew point.

### Safety:

See safety data sheet PurStone One Vital

### PROCESSING DATA

<b>Consumption</b>	0,2 kg/m <sup>2</sup>
<b>Processability</b>	30 minutes at 20 °C
<b>Full loadability</b>	4 days at +20 °C
<b>Adhesion to concrete</b>	≥ 1,5 MPa
<b>Walkability</b>	24 hours at +20 °C
<b>Application temperature</b>	+10 °C to +30 °C

**CZ: TOPSTONE s.r.o.**

Družstevní 442, 753 01 Hranice  
Česká republika  
+420 580 582 580 | info@topstone.cz  
www.topstone.cz

ISO 9001, ISO 14001

**SK: TOPSTONE Slovensko s.r.o.**

prevádzka Vrbovská cesta 123  
921 01 Piešťany  
+421 918 459 563 | info@topstone.sk  
www.topstone.sk

**PARTNER / DEALER:**

*The information and data contained in this document has been compiled to the best of our knowledge and experience. No damage or deterioration can occur when our products are used according to our recommended procedures on the materials for which they are intended. However, the material, the application technique and the working and operating conditions are beyond our influence and therefore our recommendations are generally valid and cannot be used as a basis for liability.*